

K A U F M A N

PRODUCT
INFORMATION

KAUFMAN
PRODUCTS
INC.

3811 CURTIS
AVENUE

BALTIMORE,
MARYLAND
21226-1131

410-354-8600
800-637-6372

www.kaufmanproducts.net

K Pro UC Epoxy Grout

Description

K Pro UC Epoxy Grout is a three-component, 100% solids, extended-pot life, and moisture-insensitive marine epoxy grout system. The extended pot life of K Pro UC Epoxy Grout sets it apart from the competition. This unique feature greatly enhances the ability to pump K Pro UC Epoxy Grout longer distances. K Pro UC Epoxy Grout can also easily be poured or used in tremie applications.

No fillers, non-reactive diluents, or solvents are used in K Pro UC Epoxy Grout. Additionally, K Pro UC Epoxy Grout may be used in fresh, salt, or brackish water, and will bond effectively to wood, concrete, steel, and fiberglass.

Uses

K Pro UC Epoxy Grout is ideal for the restoration of structural pile members in underwater applications as an epoxy grout to fill the annular space between pile jackets and pilings. Extremely flowable and easy to pump, K Pro UC Epoxy Grout is ideal for plural component pumping applications, both above and below the water line, where large volumes of epoxy grout must be placed.

K Pro UC Epoxy Grout is ideal for tremie applications, as well as for other marine applications, such as piers, sea walls, dams, bridges, and other offshore structures. K Pro UC Epoxy Grout is impact resistant as well.

Additionally, K Pro UC Epoxy Grout is also a multi-purpose system, and may be used in many other types of epoxy grout applications, in both wet and dry environments where a high strength epoxy grout is necessary.

Storage Conditions

Store dry at 40-95°F. Condition material to 65-85°F before using.

Directions

Surface Preparation

Piling surfaces must be clean and sound. Remove all grease, oil, wax, curing compound, sealers, laitance, loose concrete or wood, rust, marine growth, and other foreign matter that would act as a bond-breaker. Water-blasting and/or a wire brush are the preferred methods of preparation to provide an open textured profile. A concrete surface profile (CSP) as per ICRI Guideline 310.2R of 6-9 must be achieved for proper bonding adhesion to concrete.

Test Methods	High Flow Mix Ratio Test Results	Standard Mix Ratio Test Results
Product Information		
Mix Ratio	2:1 by Volume	
Gel Time (ASTM C-881)	50-60 Minutes	
Viscosity (ASTM D-2556)	400-600 cps.	
Shelf Life	2 Years	
Density (ASTM C-905)	119 lbs./ft ³	132 lbs./ft ³
VOC Content	0 Grams/Liter	
Technical Information		
Bond Strength (ASTM C-882) 2 Days Moist Cure 14 Days Moist Cure 14 Days Air Cured	1,500 psi. 2,500 psi. 2,300 psi.	
Compressive Strength (ASTM D-695) 1 day 7 Days	4,000 psi. 9,000 psi.	
Compressive Strength (ASTM C-579 Procedure B) 1 Day 7 Days 28 Days	9,000 psi. 13,000 psi. 13,500 psi.	10,000 psi. 13,400 psi. 13,800 psi.
Flexural Strength (ASTM C-580) 7 Days	4,000 psi.	3,500 psi.
Tensile Strength (ASTM C-307)	1,700 psi.	1,600 psi.
Tensile Strength (ASTM D-638) 7 Days	7,500 psi.	
Tensile Elongation (ASTM D-638)	4-7%	
Water Absorption (ASTM D-570)	0.07% at 24 Hours	
Effective Bearing Area (ASTM C-1339)	>85%	

Steel surfaces must be prepared by water-jetting or other mechanical means required to achieve SSPC-SP 12/NACE 5 WJ-4. Wood surfaces may best be prepared by high-pressure water blasting to achieve a sound surface free of contaminants. All areas that have excessive section loss, whether it is concrete, steel, or wood, should be repaired or replaced.

Proportioning/Mixing

The volumetric ratio of K Pro UC Epoxy Grout is 2:1 (A:B) for the epoxy to hardener. To mix, proportion two parts A and 1 part B into a clean pail. Mix thoroughly for 2-3 minutes with a paddle on a low speed (400-600 rpm) drill until blend is a uniform color. Take care to avoid entrapping air in the mixed material. Slowly add the C Component to produce either a flowable or a stiff consistency epoxy grout. Mix all three components for 2-3 minutes or until uniformly blended.

K Pro UC Epoxy Grout may be pumped. The annular space between the pile jacket and piling must be a minimum of ½'. Install pumping ports at 90° from the tongue and groove joint, alternating sides. The first port should be at least 9-12" from the bottom. Place subsequent ports at a maximum of 5 feet vertical spacing, while alternating sides. Always pump from the lowest port, and move upwards. Never exceed 10 feet pumping distance between ports. All submerged forms should be inspected prior to epoxy mortar application to prevent leaks or failures, and should be checked during placement.

K Pro UC Epoxy Grout may be poured or used in tremie applications; however it is imperative that the hose be placed at the bottom of the form. The tremie hose shall be retracted as the annular space fills.

When ether pumping, pouring, or the tremie method of application, the water will be displaced out the top of the form.

Continue to fill the annular space until undiluted epoxy grout overflows from the sleeve. Once the epoxy mortar has cured adequately, top off with epoxy mortar, and finish as desired.

Underwater product placement should only be attempted by experienced diving contractors. *Read Safety Data Sheet before using.* Please refer to the *General Epoxy Instructions* for complete details on proper application during cold and hot weather. Take care always to prevent spills.

Packaging/Yield

High Flow Epoxy Grout: One 3-gallon unit of epoxy and hardener when mixed with two bags of aggregate will yield 1.03 ft³ of flowable epoxy grout.

Standard Flow Epoxy Grout: One 3-gallon unit of epoxy and hardener when mixed with three bags of aggregate will yield 1.36 ft³ of a stiff consistency epoxy grout.

Technical Information

Test results were achieved under laboratory conditions. Statistical variations will occur based upon mixing methods, temperature & humidity, test methodology, site conditions, curing conditions, application methods, and equipment.

Precautions

Do not thin K Pro UC Epoxy Grout. The contractor shall use the test method prescribed ACI 503R to determine that the preparation produced a surface capable of providing tensile bond strength greater than 250 psi. If stored below 40°F, some settling and lumping may appear. Do not use in ambient temperatures below 45 degrees Fahrenheit.

For professional use only. Not for sale to or use by the general public.

LIMITED WARRANTY We warrant our products to be of good quality and will replace material proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement, Kaufman Products, Inc makes no warranty or guarantee, expressed or implied, including warranties of fitness or merchantability, respecting its products, and Kaufman Products, Inc shall have no other liability with respect hereto. User shall determine the suitability of the product or the intended use and assume all risks and liability in connection thereto. Our salespeople, distributor, and their salespeople have no authority to change the printed recommendations concerning the use of our products.