

# K A U F M A N

PRODUCT  
INFORMATION

KAUFMAN  
PRODUCTS  
INC.

3811 CURTIS  
AVENUE

BALTIMORE,  
MARYLAND  
21226-1131

410-354-8600  
800-637-6372  
www.kaufmanproducts.net

## Krystal 15 Emulsion

### Description

Krystal 15 Emulsion is a state of the art, water emulsion of styrene acrylate copolymers. This high quality polymer produces a VOC compliant compound for curing freshly placed concrete. This product provides a cure and seal while assuring total resistance to yellowing from ultraviolet exposure. It is particularly suited for concrete where VOC requirements or safety concerns make solvent based systems inappropriate

In addition, this product is unique in that it has built in freeze/thaw protection. While it will solidify if frozen, after thawing and gentle stirring, it will be as good as new.

### Uses

This product provides a totally clear membrane for new concrete or old. It will make clean up at the end of the job, much easier. It provides an alternative to solvent-based materials where fumes may be objectionable. It, also, helps minimize spalling of exterior concrete. Krystal 15 Emulsion complies with both EPA & AIM Regulations from LADCO & OTC.

### Physical Characteristics 75°F & 50% R.H.

Color	Wet: White Dry: Clear
NVM	15%
Viscosity	40-90 cps
Specific Gravity	1.01
Dry Time	1-2 hours
Recoat Time	2-24 hours
Foot Traffic	2-4 hours
Wheel Traffic	6-10 hours
VOC Content	< 350 g/L
Moisture Loss (ASTM C-156)	<0.45 kg/m <sup>2</sup>
Flash Point	>500°F
Odor	Slight solvent
Shelf Life	1 year in unopened container
Specular Gloss (ASTM D-523)	75%

### Compliances

ASTM C-309, Type I or ID, Classes A & B  
Meets the Class A requirements for UV stability  
as per ASTM C-1315, Section 6.4.1

### Packaging

208.16 Liters (55 gal. drum)  
18.93 Liters (5 gal. pail)

### Coverage Rate

Curing/Sealing 200-300 ft<sup>2</sup>/gl.  
New Concrete

Sealing/Dustproofing 300-400 ft<sup>2</sup>/gl.  
Old Concrete

### Application

Surface should be clean, free of grease, oil, standing water and other foreign matter as per ASTM D-4258. Apply evenly with clean sprayer with nozzles specifically designed for curing compounds, such as Chapin nozzle # 1-5937 or equal. Apply as soon as the surface is sufficiently hard, so that it will not be marred. Do not puddle. Short napped rollers may also be used.

If using as a curing compound, apply as soon as finishing operations are completed and the surface will not be marred by the application. Do not apply over puddles. Subsequent coats should be applied on top of *dry* Krystal 15 Emulsion.

Clean equipment with clean water before the product dries. After drying, strong solvents, such as Xylene, MEK, or Toluene will soften and help to remove the film.

The use of SureGrip, added directly to Krystal 15 Emulsion prior to application, will provide a slip-resistant surface.

## **Precautions**

Both Krystal 15 Emulsion and the substrate must be at least 42°F before application. Not designed for immersion in strong chemicals or prolonged exposure to gas.

If applied too thick, the film will not dry properly and will leave a white film. Do not subject the coating to rain or water until it dries hard.

All clear sealers produce an uneven gloss on existing concrete due to uneven porosity of the surface. Never apply over puddles. Although compatible with many carpets, tile and floor covering adhesives, a test section is recommended for questionable adhesives. This material is freeze/thaw stable. However, if exposed to freezing, stir well before use. Read Safety Data Sheet before using.

For more complete instructions, please refer to "*Recommended Field Procedures for Curing & Sealing Compounds.*"

## **Technical Information**

The following results were achieved under laboratory conditions. Statistical variations will occur based upon mixing methods, temperature & humidity, test methodology, site conditions, curing conditions, application methods, and equipment.

For professional use only. Not for sale to or use by the general public.

LIMITED WARRANTY We warrant our products to be of good quality and will replace material proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement, Kaufman Products, Inc makes no warranty or guarantee, expressed or implied, including warranties of fitness or merchantability, respecting its products, and Kaufman Products, Inc shall have no other liability with respect hereto. User shall determine the suitability of the product or the intended use and assume all risks and liability in connection thereto. Our salespeople, distributors and their salespeople have no authority to change the printed recommendations concerning the use of our products.