

# K A U F M A N

PRODUCT  
INFORMATION

KAUFMAN  
PRODUCTS  
INC.

3811 CURTIS  
AVENUE

BALTIMORE,  
MARYLAND  
21226-1131

410-354-8600  
800-637-6372  
[www.kaufmanproducts.net](http://www.kaufmanproducts.net)

## SurePoxy HMLV Class B

### Description

SurePoxy HMLV Class B is a 100% solids, two component, moisture-insensitive, epoxy resin system. This is a low viscosity, multi-purpose product that can be applied neat or filled with aggregate in temperatures as low as 32°F.

### Uses

SurePoxy HMLV Class B is recommended for use in temperatures of 32°F-65°F, as a low-viscosity, penetrating adhesive. SurePoxy HMLV Class B is ideal for pressure injection high modulus grouting. When mixed with SurePoxy Aggregate, it provides an excellent setting bed for precast concrete, marble and granite or a repair mortar.

#### Typical Properties

Uncured	75°F	45°F
Mixing Ratio	2:1 by volume	2: 1 by volume
Color	A-straw B-amber Mixed-amber	A-straw B-amber Mixed-amber
Viscosity	350 cps	1200-1700 cps
Shelf Life	2 year min.	2 year min.
Pot Life.		
neat 1 lb.	6 min.	15 min.
Tack-free	20 min.	90 min. approx.
(thin film)Neat		
Final Cure	3 day	7 days
-----		
<b>Fully Cured</b>		
HDT (ASTM D-648)		50°C
Bond Strength (ASTM C-882)		1,885 psi min.
Compressive Strength		13,000 psi @ 3 hrs.
5:1 mortar ASTM D-695		15,000 psi @ 7 days
Compressive Yield Strength		13,000 psi min.
Compressive Modulus		500,000 psi min.
Tensile Strength		7,000 psi min.
& elongation		1-5%
Flexural Strength		15,000 psi min.
Flexural Modulus		450,000 psi min.
Shrinkage, ASTM C-883		.002 max

All values approximate - will vary with temperature and humidity.

### Specifications

ASTM C-881, Types I, II, IV and V, Grade 1, Class B  
AASHTO M-235, Types I, II, IV & V, Grade 1, Class B

### VOC

0 grams/Liter

### Packaging

16.5 oz. cartridge  
3 gallon unit

### Storage Conditions

Store dry at 40-95°F. Condition material to 40-60°F before using.

### Directions

#### Surface Preparation

Concrete - Surface must be clean and sound. It may be dry or damp but free of standing water. Remove laitance, and all foreign matter as per ASTM D-4258 and D-4259. Waterblasting followed by shotblasting is the preferred method of preparation, to provide a fractured aggregate profile. Also satisfactory are sandblasting or shotblasting individually. Acid etching according to ASTM D-4260 with Kaufman Products Concrete Floor Etch or 15-20% muriatic acid solution can be used as an alternative. Wash acid and loose mortar off with high-pressure water until slush is removed. Test with litmus paper to be sure acid is removed. Final rinse with 1% ammonia solution is beneficial for final rinsing after acid. Steel - Sandblast to appropriate finish.

### Proportioning/Mixing

The volumetric ratio of SurePoxy HMLV Class B is 2:1. To mix, proportion 2 parts A and 1 part B into a clean pail. Mix thoroughly for 1 minute with paddle on low speed (400-600 rpm) drill until blend is a uniform color. Add up to approximately 7 parts by volume SurePoxy Aggregate to 1 part neat SurePoxy HMLV Class B to produce a mortar. Mix thoroughly.

# K A U F M A N

PRODUCT  
INFORMATION

KAUFMAN  
PRODUCTS  
INC.

3811 CURTIS  
AVENUE

BALTIMORE,  
MARYLAND  
21226-1131

410-354-8600  
800-637-6372  
[www.kaufmanproducts.net](http://www.kaufmanproducts.net)

## Application

Grout Cracks - Gravity feed SurePoxxy HMLV Class B into horizontal cracks, pressure inject into vertical or overhead cracks, after sealing. Anchor bolts - Use either neat or with SurePoxxy Grout Aggregate, added at the rate of 5-7 parts to 1 part of SurePoxxy HMLV Class B by volume.

Mortar - Mix with SurePoxxy Mortar Aggregate, added at the rate of 5-7 parts to 1 part SurePoxxy HMLV Class B by volume.

## Precautions

Do not thin SurePoxxy HMLV Class B. Do not apply to surfaces below 40°F, unless checking with the factory first. Pot life will vary due to different temperatures. . If used at temperatures greater than 60°F, the reaction time is very fast and subsequently should be extended with aggregates when any sizeable mass is utilized. Likewise when using at temperatures approaching 32F, the product should not be extended with aggregate. Contractor shall use the test method prescribed in ACI 503R to determine that the preparation produced a surface capable of providing tensile bond strength greater than 250 psi. During cold weather periods, be sure frost and/or ice is off concrete before applying SurePoxxy HMLV Class B because it cannot adhere well to ice crystals. SurePoxxy HMLV Class B is a vapor barrier after cure. *Read Safety Data Sheet before using.* Please refer to the *General Epoxy Instructions* for complete details on proper application during cold and hot weather.

## Technical Information

Test results were achieved under laboratory conditions. Statistical variations will occur based upon mixing methods, temperature & humidity, test methodology, site conditions, curing conditions, application methods, and equipment.

For professional use only. Not for sale to or use by the general public.

LIMITED WARRANTY We warrant our products to be of good quality and will replace material proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement, Kaufman Products, Inc makes no warranty or guarantee, expressed or implied, including warranties of fitness or merchantability, respecting its products, and Kaufman Products, Inc shall have no other liability with respect hereto. User shall determine the suitability of the product or the intended use and assume all risks and liability in connection thereto. Our salespeople, distributors and their salespeople have no authority to change the printed recommendations concerning the use of our products.