

K A U F M A N

PRODUCT
INFORMATION

KAUFMAN
PRODUCTS
INC.

3811 CURTIS
AVENUE

BALTIMORE,
MARYLAND
21226-1131

410-354-8600
800-637-6372
www.kaufmanproducts.net

SureCure 25 Clear & Brown

Description

SureCure 25 is an oil-base, high-solids version of our well-known SureCure line of concrete curing & sealing treatments. It contains increased amounts of acrylic-modified, styrene co-polymer solids for longer lasting sealing of the concrete surface, as well as retaining more moisture for better concrete hydration and curing. SureCure 25 is available either clear or in a transparent brown version to enhance the “wet look” and beauty of natural stone in exposed aggregate surfaces.

Uses

This tough co-polymer concrete treatment is designed for exterior and interior applications, above and below grade. Easily applied, SureCure 25 provides the maximum protection for the concrete surface from construction stains. It is compatible with all conventional carpet and resilient flooring adhesives. It is recommended for curing, hardening, dustproofing and sealing of both new and old concrete surfaces, including exposed aggregate.

Compliances

ASTM C-309, Type I, Class B
ASTM C-1315, Type I, Class B

Safety

VOC - 571 gm/Liter. Complies with specifications.
Flash Point - 110°F

Technical @75°F

NVM	25% min.
Dry Time	<1 hour
UV degradation	passes
Color	1 Gardner, max
Adhesion, ASTM D 4541	passes
Alkali & Acid Resistance	passes

Packaging

55 gal. drums (208 liters)
5 gal. pails (18.9 liters)
1 gal. cans (3.78 liters)

Directions

Fresh Concrete - SureCure 25 should be applied within 1-2 hours after completion of the finishing operation or as soon as possible after surface water has disappeared. Coat surface uniformly, leaving no pinholes or gaps, at a coverage rate of 300 - 350 sq. ft. per gallon. Apply with hand sprayers equipped with nozzles specifically designed for high solids curing compounds, such as Chapin nozzle #1-5937 or equal. Apply as soon as the surface is sufficiently hard, so that it will not be marred. Do not puddle. If using a power sprayer, we recommend Kaufman Products Power Sprayer, because it was specifically designed for quick and even applications of emulsions as well as oil thinned cures. The use of a natural bristle brush or short nap rollers can also be used.

Apply second coat, after previous coat has dried at least overnight. Be sure both coats are dry and hard before opening slabs to traffic.

Aged Concrete - Remove all foreign matter. Apply as described above, however coverage rate may vary from 300-500 sq. ft. per gallon depending on texture and porosity of surface.

Notes

All application equipment should be cleaned with SAC. Do not thin. Do not apply to surfaces meant to receive a cementitious topping. When clear is used on exterior concrete, an amber color may develop. Especially, when applied at heavier application rates. Stir SureCure 25 Brown well before use. Read Material Safety Data before using. This is an industrial product. It is not offered for residential or consumer use.

For more complete instructions, please refer to “*Recommended Field Procedures for Curing & Sealing Compounds.*”

F:\Eng. Literature w-out Heading\503.docFeb-07

For professional use only. Not for sale to or use by the general public.

LIMITED WARRANTY We warrant our products to be of good quality and will replace material proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement, Kaufman Products, Inc makes no warranty or guarantee, expressed or implied, including warranties of fitness or merchantability, respecting its products, and Kaufman Products, Inc shall have no other liability with respect hereto. User shall determine the suitability of the product or the intended use and assume all risks and liability in connection thereto. Our salesmen, distributors and their salesmen have no authority to change the printed recommendations concerning the use of our products.