

# K A U F M A N

PRODUCT  
INFORMATION

KAUFMAN  
PRODUCTS  
INC.

3811 CURTIS  
AVENUE

BALTIMORE,  
MARYLAND  
21226-1131

410-354-8600  
800-637-6372

[www.kaufmanproducts.net](http://www.kaufmanproducts.net)

## SureCure 30

### Description

SureCure 30 is our highest grade of our long time famous SureCure concrete treatment. It contains increased amounts of acrylic modified styrene copolymer solids for better sealing of the concrete surface from stains and provides a more dustproofed slab

### Uses

This tough copolymer concrete treatment is designed for exterior and interior applications, above and below grade. Easily applied, SureCure 30 provides a premium performance, long lasting shine to the floors. It is compatible with conventional carpet and resilient flooring adhesives. It is recommended for curing, hardening, dustproofing and sealing of both new and old concrete surfaces. As a sealer for existing concrete, it provides a very durable, glossy film resistant to mild acids alkalis.

### Compliances

ASTM C-309, Type I, Class B  
ASTM C-1315, Type I, Class B

### Safety

VOC - 500 gm/L. Complies with specifications.  
Flash Point - 105°F

### Technical, Clear @75°F

NVM	30% min.
Viscosity	100 cps. approx.
Dry Time	<1 hour
UV degradation	passes
Color	1 Gardner, max.
Adhesion, ASTM D 4541	passes
Alkali & Acid Resistance	passes

### Packaging

55 gal. drums (208 liters)  
5 gal. pails (18.9 liters)

### Directions

Fresh Concrete - SureCure 30 should be applied within 1-2 hours after completion of the finishing operation or as soon as possible after surface water has disappeared. Coat surface uniformly, leaving no pinholes or gaps, at a coverage rate of 350 - 450 sq. ft. per gallon. Apply with hand sprayers equipped with nozzles specifically designed for high solids curing compounds, such as Chapin nozzle 1-5937 or equal. Apply as soon as the surface is sufficiently hard, so that it will not be marred. Do not puddle. If using a power sprayer, we recommend Kaufman Products Power Sprayer, because it was specifically designed for quick and even applications of emulsion as well as oil thinned cures.

Apply second coat, after previous coat has dried at least overnight. Be sure both coats are dry and hard before opening slabs to traffic. Aged Concrete - Remove all foreign matter. Apply as described above, however coverage rate may vary from 400-500 sq. ft. per gallon depending on texture and porosity of surface.

### Notes

Clean equipment with SAC. Do not thin. Do not apply to surfaces meant to receive a cementitious topping. When used on exterior concrete an amber color may develop when applied at heavier coverage rates. If a completely non yellowing sealer is desired, we recommend using Krystal 25. Not only is it non yellowing, but it is also water based. Do not apply to surfaces meant to receive a cementitious topping. Read Material Safety Data before using. This is an industrial product. It is not offered for residential or consumer use.

For more complete instructions, please refer to "Recommended Field Procedures for Curing & Sealing Compounds."

F:\T\Eng. Literature w-out Heading\505.doc Feb-07

For professional use only. Not for sale to or use by the general public.

LIMITED WARRANTY We warrant our products to be of good quality and will replace material proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement, Kaufman Products, Inc makes no warranty or guarantee, expressed or implied, including warranties of fitness or merchantability, respecting its products, and Kaufman Products, Inc shall have no other liability with respect hereto. User shall determine the suitability of the product or the intended use and assume all risks and liability in connection thereto. Our salesmen distributors and their salesmen have no authority to change the printed recommendations concerning the use of our products.