

INFORMATION

KAUFMAN PRODUCTS INC. 3811 CURTIS AVENUE 410-354-8600 800-637-6372 www.kaufmanproducts.net

Krystal 25 Emulsion

Description

Krystal 25 Emulsion is a state of the art, waterbased, and low VOC, curing & sealing compound. This high quality polymer produces a VOC compliant compound for curing freshly placed concrete. This product provides a quality cure and seal while assuring total resistance to yellowing from ultraviolet exposure. It is particularly suited for concrete where VOC requirements or safety concerns make solvent based systems inappropriate.

In addition, this product is unique in that it has built in freeze/thaw protection. While it will solidify if frozen, after thawing and gentle stirring, it will be as good as new. Krystal 25 Emulsion is a UV resistant version of our long famous SureCure 25 Emulsion.

Uses

Krystal 25 Emulsion will cure, harden, dustproof and seal concrete surfaces. This glossy, nonyellowing, premium quality curing compound & sealer is recommended over all types of concrete floor surfaces, inside or out, above, on, or below grade. It provides an alternative to solvent-based materials where solvent fumes may be objectionable. In addition, Krystal 25 Emulsion may be used on slate, flagstone, brick pavers, stamped concrete, artificial stone, and exposed aggregate

Once it is dry, it is resistant to water, dilute acids and alkali, oils, and fats, as well as air borne contaminants. Krystal 25 Emulsion complies with both EPA & AIM Regulations from LADCO & OTC.

Physical Characteristics 75°F & 50% R.H.		
Color	Wet: White	
	Dry: Clear	
NVM	25%	
Viscosity	40-90 cps	
Specific Gravity	1.01	
Dry Time	1-2 hours	
Recoat Time	2-24 hours	
Foot Traffic	2-4 hours	
Wheel Traffic	6-10 hours	
VOC Content	< 350 g/L	
Moisture Loss (ASTM C156)	<.0.30 kg/m ²	
Specular Gloss (ASTM D-523	3) 88%	
Flash Point	NA	
Odor	Mild latex paint	
Shelf Life	1 year in unopened	
	container	

Chemical Resistance

12-hour immersion

Sulfuric Acid, 28%	NR
Sulfuric Acid, 10%	R
Acetic Acid, 28%	NR
Acetic Acid, 10%	R
Hydrochloric Acid, 28%	NR
Hydrochloric Acid, 10%	R
Nitric Acid, 28%	NR
Nitric Acid, 10%	R
Sodium Hydroxide, 50%	R
Potassium Hydroxide, 50%	R
Calcium Chloride	R
Gasoline	NR
Xylene	NR
Mineral or Motor Oils	R
Vegetable Oils	R
-	

MARYLAND

21226-1131

Not Recommended NR Recommended R

Compliances

ASTM C-309, Type I, Classes A & B ASTM C-1315, Type I, Class A

Packaging

275 gallon tote 55 gallon drum 5 gallon pail 1 gallon jug

Coverage Rate

0-350 ft ² /gl.
-
0-400 ft ² /gl.
0-400 ft²/gl.

Application

Surface should be clean, free of grease, oil, standing water and other foreign matter as per ASTM D-4258. Apply evenly with clean sprayer with nozzles specifically designed for high solids curing compounds, such as Chapin nozzle # 1-5937 or equal. Apply as soon as the surface is sufficiently hard, so that it will not be marred. Do not puddle. Short-napped rollers may also be used. If using as a curing compound, apply as soon as finishing operations are completed and the surface will not be marred by the application. Do not apply over puddles. Subsequent coats should be applied on top of *dry* Krystal 25 Emulsion.

Although compatible with most carpet, tile, and floor covering adhesives, a test section is recommended for questionable adhesives.

Clean equipment with clean water before the product dries. After drying, strong solvents, such as Xylene, MEK, or Toluene will soften and help to remove the film.

The use of SureGrip, added directly to Krystal 25 Emulsion prior to application, will provide a slip-resistant surface.

Precautions

Both Krystal 25 Emulsion and the substrate must be at least 45° F before application. Not designed for immersion in strong chemicals or prolonged exposure to gas. All coatings may be slippery when wet. If intended to be used on smooth surfaces, in wet areas, apply 25 lb. per 100 ft² of special aggregate on surface while coating is still wet. Allow to cure thoroughly before subjecting to full use.

If applied too thick, the film will not dry properly and will leave a white film.

Do not subject the coating to rain or water until it dries hard.

All clear sealers produce an uneven gloss on existing concrete due to uneven porosity of the surface.

This is especially evident when used on surfaces such as brick, pavers, and natural and artificial stone. Never apply over puddles. Although compatible with most carpet, tile and floor covering adhesives, a test section is recommended for questionable adhesives. This material is freeze/thaw stable, however if exposed to freezing, stir well before use. Read Safety Data Sheet before using.

For more complete instructions, please refer to "Recommended Field Procedures for Curing & Sealing Compounds."

Technical Information

The following results were achieved under laboratory conditions. Statistical variations will occur based upon mixing methods, temperature & humidity, test methodology, site conditions, curing conditions, application methods, and equipment.

For professional use only. Not for sale to or use by the general public.

LIMITED WARRANTY We warrant our products to be of good quality and will replace material proved detective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement, Kaufman Products, Inc makes no warranty or guarantee, expressed or implied, including warranties of fitness or merchantability, respecting its products, and Kaufman Products, Inc shall have no other liability with respect hereto. User shall determine the suitability of the product or the intended use and assume all risks and liability in connection thereto. Our salespeople, distributors, and their salespeople have no authority to change the printed recommendations concerning the use of our products.