

# K A U F M A N

PRODUCT  
INFORMATION

KAUFMAN  
PRODUCTS  
INC.

3811 CURTIS  
AVENUE

BALTIMORE,  
MARYLAND  
21226-1131

410-354-8600  
800-637-6372  
www.kaufman  
products.net

## Silicure Concentrate

### Description

Silicure Concentrate is a clear, concentrated, sprayable, VOC compliant concrete curing aid, hardener, and dustproofing agent. Silicure Concentrate is nonflammable and odorless, making it ideal for interior use. **Silicure Concentrate, once diluted, meets the moisture retention properties of ASTM C-309, when used on hard troweled concrete.** Silicure Concentrate will both cure and penetrate to harden freshly placed concrete in one simple step. Silicure Concentrate may also be used on aged concrete to reduce or eliminate dusting.

Silicure Concentrate leaves no residue on the concrete surface and does not prevent adhesion of subsequent coatings or floor treatments. Silicure is not dependent on breaking down or dissipating, prior to application of subsequent flooring systems.

Silicure Concentrate will not turn yellow from UV radiation. A red fugitive dye is available and can be added for ease in application.

### Uses

Silicure Concentrate is designed to be used as a curing agent, densifier, and hardener on freshly placed concrete that is to receive subsequent flooring materials. In addition, Silicure Concentrate may be used on aged concrete to reduce and/or eliminate dusting and provide an extended life to the concrete slab. Silicure Concentrate is specifically recommended for application to concrete surfaces where a hard, abrasion resistant, light to moderately heavy-duty surface is required. Ideal for use on basements, sidewalks, driveways, floor slabs, and columns.

### Compliances

VOC Compliant, including the EPA, National AIM, LADCO, OTC, CARB, and SCAQMD

ASTM C-309 Moisture Retention Requirements, when used on hard-troweled concrete.

USDA Accepted

May contribute to LEED credits.

### VOC Content

0 grams/liter

### Packaging

5 gallon pail

55 gallon drum

### Directions

#### Surface Preparation

After finishing operations and disappearance of visible surface water; enter when the surface will bear the weight of workers without damage. Apply diluted Silicure Concentrate for a stone-like finish cure. For application to recently placed concrete that has not been membrane cured, clean surface and apply. Silicure Concentrate is not meant to be applied over a membrane-cured surface.

### Application

Silicure Concentrate **MUST** be diluted with potable water and stirred for 10 minutes for uniform blending. Mix 10 gallons of Silicure Concentrate with 45 gallons of potable water. Once diluted and stirred, Silicure Concentrate may be applied by brush, soft-bristled broom, or sprayer. One coat produces a light duty surface. Service wearability increases proportionally with each additional coat. Allow each coat to dry thoroughly before application of succeeding coat. Always apply so as to form a continuous uniform film that is free of puddles. Protect adjacent metal, glass, wood, paint, and brick from contact with Silicure Concentrate. If accidentally applied to these surfaces, remove by washing with clean water immediately. Allow at least a 7-day interval before applying tile or floor adhesives over Silicure. Allow an overnight dry before traffic is permitted. Clean equipment with water immediately after use.

## Coverage Rates

Coverage is influenced by surface conditions and porosity. Coverage rates listed below are ft<sup>2</sup>/gallon.

Area	Rough Finish	Normal Finish	Hard Finish
Freshly placed concrete	300	400	500
Recently placed concrete	200	300	400
Aged concrete	150	200	250
Aged Terrazzo		500	
Vertical surfaces	200	300	
Succeeding coats			

Reduce coverage rates from above for each succeeding coat.

## Precautions

Protect Silicure from freezing. If it does freeze, allow to thaw. Stir or agitate uniformly before using. Do not apply if the temperature is less than 40oF. Prevent Silicure from into contact with glass, brick, aluminum, painted surfaces, or other glazed surfaces. Not recommended over colored concrete surfaces. Do not over apply or leave puddles, as this will cause the formation of white crystals on the concrete. If this occurs, stop the application and flush off with water immediately. Mechanical abrasion is the only way to remove the crystals once dried.

*Read Safety Data Sheet before using.*

## Technical Information

Test results were achieved under laboratory conditions. Statistical variations will occur based upon mixing methods, temperature & humidity, test methodology, site conditions, curing conditions, application methods, and equipment.

For professional use only. Not for sale to or use by the general public.

LIMITED WARRANTY We warrant our products to be of good quality and will replace material proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement, Kaufman Products, Inc makes no warranty or guarantee, expressed or implied, including warranties of fitness or merchantability, respecting its products, and Kaufman Products, Inc shall have no other liability with respect hereto. User shall determine the suitability of the product or the intended use and assume all risks and liability in connection thereto. Our salespeople, distributors and their salespeople have no authority to change the printed recommendations concerning the use of our products.